

Wood Density

Record Details

Green Density (g/cm3):	NA
Airdry Density (g/cm3):	0.64
Ovendry Density (g/cm3):	9.68
Tree height avg:	NA
Tree height min:	NA
Tree height max:	NA
Tree DBH avg:	NA
Tree DBH min:	NA
Tree DBH max:	NA
Wood mass:	NA
Mass Moisture Content:	NA
Wood volume:	NA
Volume Moisture Content:	NA
Coefficient of Retraction:	NA
Fiber Saturation Point (%):	NA
Methodology Green:	NA
Methodology Airdrie:	Direct measurement of the dimension of the specimen
Methodology Owendry:	Water displacement method
Bark:	NA
Moisture Content Density:	NA
Data origin:	Biblio
Data type:	Average
Samples per tree:	NA
Number of trees:	NA
Standard Deviation:	NA
Min of Wood Density:	NA
Max of Wood Density:	NA
Height sample collected:	NA
Bark distance:	NA
Convert BD:	NA
CV:	NA

Idendification

Tree type: Tree

Vegetation type: NA

Taxonomy

Family: Lythraceae **Genus:** Lagerstroemia **Species:** Lagerstroemia speciosa **Subspecies:** NA **Local Names:** Bombayanjan

Locations

Location Name: Unknown

Division: Unknown

District: Unknown

FAO Biome: Unknown

Upazila: NA

BFI Zone: Unknown

Union: NA

Bangladesh Agroecological Zone: Unknown

Latitude: 0

Longitude: 0

Reference

Reference: Sattar, M.A. (1981). Some physical properties of 116 Bangladeshi timbers. Bulletin 7, Wood seasoning series, Forest Research Institute, Chittagong Bangladesh.

Author: Sattar, MA

Year: 1981

Contributor

Contributor: Bangladesh Forest Department

Dataset

Dataset: Wood Density

@Copyright-2018 Bangladesh Forest Department