

Wood Density

Record Details

Green Density (g/cm3):	0.56
Airdry Density (g/cm3):	0.58
Ovendry Density (g/cm3):	0.62
Tree height avg:	NA
Tree height min:	NA
Tree height max:	NA
Tree DBH avg:	NA
Tree DBH min:	NA
Tree DBH max:	NA
Wood mass:	NA
Mass Moisture Content:	NA
Wood volume:	NA
Volume Moisture Content:	NA
Coefficient of Retraction:	NA
Fiber Saturation Point (%):	NA
Methodology Green:	Water displacement method
Methodology Airdrie:	Direct measurement of the dimension of the specimen
Methodology Owendry:	Water displacement method
Bark:	NA
Moisture Content Density:	NA
Data origin:	Biblio
Data type:	Average
Samples per tree:	54
Number of trees:	NA
Standard Deviation:	NA
Min of Wood Density:	NA
Max of Wood Density:	NA
Height sample collected:	NA
Bark distance:	NA
Convert BD:	NA
CV:	NA

Idendification

Tree type: Tree

Vegetation type: NA

Taxonomy

Family:	Genus:	Species:	Subspecies:	Local Names:
Sterculiaceae	Pterospermum	Pterospermum acerifolium	NA	Fasya udal

Locations

Location Name:	Unknown		
Division:	Unknown		
District:	Unknown	FAO Biome:	Unknown
Upazila:	NA	BFI Zone:	Unknown
Union:	NA	Bangladesh Agroecological Zone:	Unknown
Latitude:	0		
Longitude:	0		

Reference

Reference: Sattar, M.A., Bhattacharjee D.K., Kabir, M.F. (1999). Physical and mechanical properties and uses of timbers of Bangladesh. Bangladesh Forest Research Institute, Chittagong, Bangladesh.

Author: Sattar MA, Bhattacharjee DK, Kabir MF

Year: 1999

Contributor

Contributor: Bangladesh Forest Department

Dataset

Dataset: Wood Density

@Copyright-2018 Bangladesh Forest Department